



## **BIOCOURT 72008**

## **TECHNICAL DATA SHEET**

The shock-absorbing rubber substrate 4mm-10mm in thickness is used as sport surface underlay in basketball, volleyball, tennis and handball courts. It is resistant to time and weather conditions, helps in doing sports with safety, prevents injuries from shocks and improves the ball rebound. It is easily applied to a clean flat surface using a two- component polyurethane adhesive.

At the top it is coated with acrylic or self-leveling polyurethane in order to create the final use surface.



## **PRODUCT CHARATERISTICS**

Material: Recycled fine rubber granules bonded with PU binder

| Colour            | Black     |                        |
|-------------------|-----------|------------------------|
| Density           | 720 ± 5%  | DIN EN ISO 845         |
| kg/m <sup>3</sup> |           |                        |
| Thickness         | 10 ± 1,5% | DIN 53534              |
| mm                |           |                        |
| Roll length       | 5         | or according to demand |
| m                 |           |                        |
| Roll width        | 1.20      |                        |
| m                 |           |                        |
| Roll area         | 6.00      |                        |
| $m^2$             |           |                        |
| Area weight       | 5.76      |                        |
| kg/m <sup>2</sup> |           |                        |

| MECHANICAL PERFORMANCES    |      |              |  |  |  |
|----------------------------|------|--------------|--|--|--|
| Tensile strength.<br>N/mm² | 0.50 | EN ISO 1798  |  |  |  |
| Elongation at break min%   | 50   | EN ISO 1798  |  |  |  |
| Force reduction            | NR   | EN ISO 14904 |  |  |  |
| Shock absorption %         | 26   |              |  |  |  |







## **BIOCOURT 72008**

| <b>Temperature range</b> °C | -30° to +80° C      |  |
|-----------------------------|---------------------|--|
| Fire resistance             | Depending on PU top |  |
|                             | coating             |  |

| н                   | EALTH PROTECTION |              |
|---------------------|------------------|--------------|
| VOC Emission Rating | A+               | DIN EN 16516 |
| Nitrosamine         | compliant        | DIK Method   |
| PAH                 | compliant        | DIN EN 18287 |

| PACKAGING         |             |  |  |
|-------------------|-------------|--|--|
| Pallet dimension  | 120x120x120 |  |  |
| cm x cm x cm      |             |  |  |
| Rolls per Pallet  | 25          |  |  |
| pieces            |             |  |  |
| Weight per Pallet | 864         |  |  |
| kg                |             |  |  |
| Area per pallet   | 150         |  |  |
| m <sup>2</sup>    |             |  |  |

All data values are provided by internal control system.

